

# Polyurethane Varnish

NAME OF ENAMEL	THERMAL CLASS	SOLID CONTENT	VISCOSITY (POISE)	APPLICABL WIRE DIA. (mm)	SUITABLE OVEN TYPE	COATING METHOD	FEATURES
YPU237	E~B	30~35	0.2~0.8	0.04~0.5	H	F	For thin line coating; Low-temperature Solderable.
YPU220	B	35~40	0.5~1.6	0.1~0.5	H	F	For all diameter; Great Solderability
YPU230	B	35~50	0.5~15	0.1~1.5	H	F、D	Wild working conditions; Great Water Resistance.
YPU240	B~F	30~50	0.3~15	0.1~1.5	H	F、D	Improved Heat Shock.
YPU250	F	35~50	0.5~15	0.3~1.0	H	F、D	F class Heat Shock.
YPU255	F	25~35	0.1~0.8	0.1~0.5	H	F	F class Low-temperature Solderable.
YPU260	F	35~55	0.5~25	0.2~1.5	H、V	F、D	For toroidal coil use.
YPU280	H	35~50	0.8~20	0.1~0.5	H	F、D	H class Heat Shock.

※H : HORIZONTAL OVEN    V : VERTICAL OVEN    F : FELT    D : DIES